

AMENDMENTS TO THE CLAIMS

1-8 (Canceled)

9. (Currently amended) A polymerizable composition comprising:

a cycloolefin mixture containing 0.1 to 50% by mole of a cycloolefin having, as a substituent group, a monovalent group including an aliphatic carbon-carbon unsaturated bond,
a metathesis polymerization ~~eatalyst~~ and catalyst,
a radical generating agent, and
a chain transfer agent.

10. (Canceled)

11. (Previously presented) A resin formed object obtained by ring-opening polymerizing the polymerizable composition as claimed in claim 9.

12. (Canceled)

13. (Previously presented) A resin formed object obtained by applying the polymerizable composition as claimed in claim 9 on a supporting body, followed by ring-opening polymerizing the polymerizable composition applied.

14. (Previously presented) A resin formed object obtained by injecting the polymerizable composition as claimed in claim 9 into a cavity of a mold, followed by ring-opening polymerizing the polymerizable composition injected.

15. (Previously presented) A resin formed object obtained by impregnating a fiber reinforcement with the polymerizable composition as claimed in claim 9, followed by ring-opening polymerizing the polymerizable composition impregnated.

16. (Previously presented) A crosslinked resin formed object obtained by heating and crosslinking the resin formed object as claimed in claim 11 to the temperature higher than the peak temperature during the ring-opening polymerization.

17. (Canceled)

18. (Previously presented) A crosslinked resin composite obtained by laminating the resin formed object as claimed in claim 11 with a base material, followed by heating and crosslinking the laminate.

19. (Canceled)

20. (Currently amended) A polymerizable composition comprising:

a cycloolefin mixture containing 0.1 to 50% by mole of a cycloolefin having, as a substituent group, a monovalent group including an aliphatic carbon-carbon unsaturated bond at the terminal of the monovalent group,

a metathesis polymerization ~~eatalyst~~ and catalyst,

a radical generating agent, and

a chain transfer agent.

21. (Previously presented) The polymerizable composition according to claim 20, wherein the monovalent group is at least one selected from the group consisting of vinyl group, allyl group, acryloyl group, methacryloyl group, vinyloxy group, allyloxy group, vinyloxycarbonyl group, allyloxycarbonyl group, acryloxymethyl group, methacryloxymethyl group, vinylphenyl group and 2-propenoxycarbonylphenyloxycarbonyl group.

22. (Previously presented) The polymerizable composition according to claim 20, wherein the monovalent group is at least one selected from the group consisting of vinyl group and allyl group.